

CITAL



ONETTA / SAWN

FEATURES

ORIGIN Europe

STONE Sedimentary Limestone

CHARACTERISTICS Brown, bronze, and cream fine grain background, with salt and pepper-like texture showing dark browns, blacks and light cream tones.

SIZE 3/8" (1cm), 1/2" (1.2cm), 3/4" (2cm), 1 1/4" (3cm)

CUSTOM SIZES MADE TO ORDER

RECOMMENDED USES High traffic internal/external flooring, internal/external walls, fireplace, column, moulding

POSSIBLE FINISHES Honed, Polished, Brushed, Sandblasted, Sandblasted+Brushed, Flamed, Flamed+Brushed, Bush Hammered.

Finishes are specific to each marble/stone type. Please inquire for finishes available.

TECHNICAL INFORMATION

Apparent Density 2690 Kg/m³ EN 1936 **Water Absorption** 0.30% EN 13755 **Compressive Strength** average 135 Mpa EN 1926 **Bending Strength** average 15.6 Mpa EN 12372 **Abrasion Resistance** 18.5 mm EN 14157 **Frost Resistance** 125 cycles ASTM C666

